

PROPERTIES	TEST METHOD	FEEDFRESH™
CONSTRUCTION	Extrusion laminated with scrim reinforcement	
APPEARANCE		White/Black
WEIGHT / AREA		31 lbs/msf
OXYGEN TRANSMISSION RATE	ASTM 3985	4.1 cc/m <sup>2</sup> /day
THICKNESS, NOMINAL	ASTM D 5199	7 mil
IMPACT RESISTANCE	ASTM D 1709 (A)	630 grams
*1" TENSILE STRENGTH @ BREAK	ASTM D 7003	68 lbf
ELMENDORF TEAR TEST	ASTM D 1922	> 3200 grams
PUNCTURE RESISTANCE	ASTM D 6241	150 lbs
MAXIMUM USE TEMPERATURE		180° F
MINIMUM USE TEMPERATURE		-70° F

\*Tests are an average of diagonal directions.



FeedFresh™ RB7WB is a ten-layer reinforced extrusion laminate. The outer layers contain high-strength polyethylene resins along with a barrier resin extruded into one of the layers to provide an ultra-low oxygen transmission rate. The outer layers include carbon black (black side) and UV stabilizers (white side) to increase outdoor longevity.

FeedFresh™ RB7WB is reinforced with a minimum of 1000 denier scrim laid in a diagonal pattern spaced 3/8" apart with an additional machine direction scrim every 9" across the width.

Note: To the best of our knowledge, unless stated otherwise, these are typical property values and are intended as guides only, not as specification limits. RAVEN INDUSTRIES MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage.



**RAVEN INDUSTRIES, INC. / Engineered Films Division**  
P.O. Box 5107 • Sioux Falls, SD 57117-5107  
Ph: (605) 335-0174 • Fx: (605) 331-0333  
**Toll Free: 800-635-3456**



**ISO 9001:2000**  
CERTIFIED MANAGEMENT SYSTEM

[www.ravenag.com](http://www.ravenag.com)